

Technoseal



Sprayable, easy-to-spread sealing product.



Properties:

- MS Polymer based product
- Safe to use, isocyanate and solvent-free
- Very good resistance to all weather conditions, water, oil and gasoline.
- Possible to overcoat immediately after application
- Very fast skin formation

Advantages:

- Application both on dry or wet surface
- Easy to apply even in inaccessible places
- Possible to spot weld through
- Imitates factory original look
- Can be applied in beads as well as wide layers
- Can be applied horizontally as well as vertically

Applications:

TECHNOSEAL was specially developed for bodywork applications, especially as a sprayable sealant for joints, parts connections, seams and similar places, providing identical look to the factory original. Alternatively, **TECHNOSEAL** can also be used as protection coating for bottom auto parts against abrasive elements or as sound insulation for car hoods, roofs and boots. It can also be applied on wet surface.

Order codes:

| Name | Storage code | Package | Volume / Size | Order number |
|------------|--------------|-----------|---------------|--------------|
| Technoseal | RTS | Cartridge | 290 ml | R 34904 |

Instructions for use:

1. Clean and degrease the treated surface with a suitable **RETECH** product and let air out.
2. When applying, make sure not to spill any sealant on the surface of materials.
3. Taping the surface around around the joint can prevent this.
4. Apply with the **RETECH PROGUN NEW** spray gun.
5. Adjust the spray gun according to its instruction manual.
6. Can be varnished immediately "wet-on-wet" or when completely cured.
7. For optimal result, we recommend applying varnish within 72 hours after application.

ONLY FOR PROFESSIONAL AND INDUSTRIAL USE!

Technical data:

| | |
|------------------------------------|---------------------|
| Basis | MS Polymer |
| Colour | grey |
| Consistency | Tixotropic paste |
| Curing system | Moisture curing |
| Skin formation* (20 °C / 65% R.H.) | Ca. 30 min |
| Curing speed * (20 °C / 65% R.H.) | 2 mm/24h → 3 mm/24h |
| Density | 1,62 g/ml |
| Temperature resistance | -25 °C → 80 °C |
| Application temperature | 5 °C → 30 °C |

(*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

Chemical resistance:

Good resistance to water, aliphatic solvents, mineral oils, grease, diluted inorganic acids and alkalis.
Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Storage:

Shelf life 2 years in unopened packaging in a cool and dry storage place at temperatures between +5 °C and +25 °C.

Health and Safety:

Please read our Material Safety Data Sheet.

Declaration:

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

Address:

RETECH, s.r.o., Vackova 1541/4; Praha 5 - Stodůlky; Czech Republic
Contact address: 285 02 Suchdol u Kutné Hory cp. 212; tel./fax: +420 327 596 128; e-mail: info@retech.cz